



# CECOIS ESPECIAL FACHADAS, HIGH MECHANICAL RESISTANCE FOR CERAMIC PLACING.



## Descripción

Glue cement that mixed with water in the right moment of using, is a great adhesive for applying ceramic, glazed tiles, etc coatings on facades. Available colours: white and grey. Prices according the volume of the order.

## Aplicación

CECOIS ESPECIAL FACHADAS can be used as an adhesive for coating with ceramic pieces on facades, courtyards, diving walls, back walls and with bricks, slabs, marble, pieces made of glass, slate, roof tile, stone, etc. In addition, roofs, pools, tanks, etc.

Its special polymeric and additives content confer a very high mechanical resistance, great capacity for support the small expansions of the pieces and a very high adherences in low-absorption pieces for pavements too.

## Surface preparation

The surface must be clean, free of greases, compact, without scalin and slaightly mostened.

## Modes of application



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: desarrollo@teais.es

síguenos en:



Mixed directly with water in the recommended proportion until getting the desired consistency.

-The mix can be done manually or with a low-revolution electric mixer (400-5000rpm).

-Mixture proportions are 7 litres of water by 25 kgs sacks.

-Once the mixture is done let it rest from 3 to 5 minutes before using.

CECOIS ESPECIAL FACHADAS is spreaded with a toothed trowel spreading the quantity suitable to support coating on the opened product time (20 minutes depending the temperature, the more temperature more time can be opened).

-Placing the pieces pressing them in order to the adhesive become smooth and all the contact surface can be covered for it.

-For pieces bigger than 30x30 cm is recommended the double-glue, it means, applying the adhesive on the piece and on the support too.

When the weather is very hot or when the support is very absorbent is recommended to moisten slightly before applying.

-On pieces placing outdoor expansion joints must be foreseen by the expansion.

## Clean up

With a lot of clean water while the material keeps fresh.

## Data sheet

Powder density  $1,25 \pm 0,05$  g/cc.

Mass of density  $1,850 \pm 0,05$  g/cc.

Curing density  $1,650 \pm 0,05$  g/cc

Water absorption  $25 \pm 3\%$

Adherence  $> 0,5$  N/mm<sup>2</sup>

Colour/s Grey and white.

Type C1 T E (UNE EN 12004)

## Performance

3 kgs by sqm on 2mm layer.

## Storage



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

Tel.: 981 602 111

Fax.: 981 601 508

Email: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:



2 years in their original sacks, well closed, no exposing to extrem temperatures, saved of weatherness and in open-air and dry places.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email.: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:

