



## Descripción

Fiberglass in yarn shape joint between them by a bonding agent. Suitable for reinforcing waterproofings. It has a good deformability, adaptation to surface of application, a fast impregnation and easy handling.

## Aplication

FIBRAIS-300 is an armour made of to improving the mechanical properties of the sheets and the waterproofing based on polyester resins.

## Surface preparation

The surface must be done and without contamination.

## Modes of application

It can be applied easily on complex surfaces.

It can be impregnated quickly and without difficultly, making easy the suitable length of the threads and the high solubility of the bonding agent with the resing, the not bubble.

## Clean up

With clean water.

# Data sheet

Colour/sWhite translucent

Density300 grs/m<sup>2</sup>

Resistance to traction25 daN

Loss in fire4,6%

Humidity.-0,2 %

Solubility in styrene25 sec

CompositionFiberglass

## Performance

1,05 m<sup>2</sup> per sqm

## Storage

Indefinetely in their original rolls and well packaged, wit stable storage temperartures, between 15 to 25°C and with a relative humidity between 45 to 65%



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

☎ Telf.: 981 602 111

📠 Fax.: 981 601 508

✉ Email: desarrollo@teais.es

síguenos en:

