



VELOAIS ESPECIAL, SYNTHETIC REINFORCEMENT TO REINFORCE WATERPROOFING.



Descripción

Aplication

In indoors and outdoors both new building and restoration. In humid or dry enviroment but always with suitable paints for the required use.

Surface preparation

Not necessary

Modes of application

Apply a suitable base of paint.

Being the paint wet add VELOAIS by a foam roller avoiding air pockets and wrinkles.

Repeat successively overlapping VELOAIS from 2 to 3 cm between them (in waterproofing) or simply stop (in



decoration).

When the set paint-VELOAIS dry finishing with two hands of smooth paint or rough.

Clean up

Not necessary.

Data sheet

Density 30 gr/m²

Elongation until breaking point 35%

Resistance to longitudinal tear > 2 daN

Resistance to traction 3,5 daN.

Average thickness 0,31 mm.

Softening point +140 a +150°C

Storage

In their original rollers. In dry place protected from the weather keeps indefinitely.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

☎ Telf.: 981 602 111

📠 Fax.: 981 601 508

✉ Email: desarrollo@teais.es

síguenos en:

