



## Descripción

Steel fibers for reinforcing concrete and pavements made of concrete. TEAIS FIBRACER can be added in concrete in factory and in work as well. Fiber uses provides high mechanical resistances to concrete, high resistances against traction and flexion, increases the tenacity, reduction of the number of contraction joints. Also, the non-structural lath can be replacing by TEAIS FIBRACER. The fiber has formed ends of 30mm of length and 6 of thickness.

## Aplicación

TEAIS FIBRACER is used as concrete reinforcement on industrial paving improving the load capacity, providing high mechanical resistances against bending and tensile, increases the resistance to impact and occasional efforts, non-structural replacing, easy to dose and the mixing can be done with usual tools. In case of pavements is important to have vapour and humid barriers which avoid the capillarity moisture of indoor pavements mainly.

## Surface preparation

The surfaces where the concrete is applied is convenient that have a vapour barrier on sub-base.

## Modes of application

TEAIS FIBRACER is added in concrete on factory and in work. The addition of fibers can be done in work inside of truck-mixer manually or with support mechanical facilities.

The additional mixture time for the setting of fibers is one minute by one m<sup>3</sup> of concrete approximately. In general, the extra-time of mixing will be from 5 to 6 minutes.

-For the addition on factory the fiber can be put onto aggregates conveyor belt or directly inside of the concrete-mixer.

## Clean up

---

With plenty of clean water.

## Data sheet

---

Resistance to traction 1400 N/mm<sup>2</sup>

Length Fiber of 30 mm

Diameter Fiber 0,8 mm

## Performance

---

From 20 to 40 kg/m<sup>3</sup>

## Storage

---

In their original packages keeping them away from the weather and in a dry place.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: desarrollo@teais.es

síguenos en:

