



## Descripción

Ployester-based mortar for indoor tightness.



## Application

It is used for the formation of waterproofing barriers in cellars, elevator shafts, galleries, etc?

### Surface preparation

The surface must be dry, free of oil stains, greased, fungi and dust. In the case of mortar and concrete they must be cured over 28 days. If there are water leaks, first they must be sealed by the application of fast cement.

### Modes of application

The proportion on weight is 125A/1B. The admixture must be homogeneous and thorough. It must be applied by trowel in thickness over 10 mm. Don't finish or splice in wedge shape (unless do it immediately).

### Clean up

With DISMORPOL if the product is wet. In case of it is dry SAPAIS must be used.

# Data sheet

Densitycomp. B:  $1,18 \pm 0,02$  g/ml.

Densitycomp. A:  $1,7 \pm 0,1$  g/ml.

Open time < a 10 minutes





## Performance

20 kg per sqm

## Storage

1 year in their original packages tightly closed.



 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
 Telf.: 981 602 111  
 Fax.: 981 601 508  
 Email.: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:

