



## Descripción

Fluid mortar for using on regularisation layer in floors. MORFLUIS is used as well as a levelling layer with a thickness between 10-30 mm on concrete floors that require levelling. MORFLUIS is a fluid mortar without retraction. Grey colour.

## Aplication

MORFLUIS is fluid mortar without retraction, special for screeds on concrete floorings of 10 mm until 30 mm of thickness.

## Surface preparation

The surface where MORFLUIS is apply on must be clean, firm, free of dust. If the surface is made of absorbent materials it must be slightly moistened.

## Modes of application

Mix with water until obtain a paste with a fluid consistency.

- The mixture can be done manually or with a low-revolution electric mixer (300-500 rpm).
- Spread it on the support slightly wet with a toothed trowel with a thickness between 10 and 30mm.
- While the material is wet a spiked roller can be used in order to remove the entrained air.

## Clean up

With plenty of water while the material is wet.

# Data sheet

Water absorption 16% aprox

Powder density 1,10 grs/cc

Mass of density 2,05 grs/cc

Curing density 1,70 grs/cc

Adherence > 3 kg/cm<sup>2</sup>

Compressive resistance > 200 kg/cm<sup>2</sup>

Temperature of work From 5 to 30°C

Mix proportion

## Performance

1,8 kg/sqm per each mm of thickness.

## Storage

2 years in their original packages, protected from the weather and stored in cool and dry places.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: desarrollo@teais.es

síguenos en:

