



TRADUR, COLORED MINERAL HARDENER FOR MAKING CONCRETE PAVEMENT



Descripción

Powder product for superficial harding on soils. It is applied on the freshly paved concrete in 2 to 3 kg by sqm proportion. Once it is applied and smoothed a LACURIS coat must be applied by sprayer. Ask for another chart colours and prices.

Aplication

Parking lots and garages. Warehouses. Loading and unloading areas. Stores, commercial areas, pedestrian areas of heavy use as paths, streets, plazas, recreation, etc..

Surface preparation

The concrete must be still fresh, not definitely cured, with the purpose of allowing the incorporation of TRADUR on the surface.

Modes of application

☒ Sprinkle evenly TRADUR in two layers over the extended and evened concrete when bleed water begins to evaporate. The first layer should have a coverage of 2 kg/m² and the second one 2 or 1 kg/m², or more depending on desired colour and intensity.

During the application process it is important to getting a homogenous result and to avoid forming piles.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teais.es

síguenos en:



Should not splashing water in the surfaces on which TRADUR is applied. The finish is done by manual or mechanical troweling. (?Helicopter?)

TRADUR application should be done when is possible to walk on the concrete without leaving marks of 2 to 4 mm depth on it.

Good concrete quality with low water/cement ratios and settlements between 75 and 110 mm with cone should be used.

The concrete must have a characteristic resistance of at least 250 kg / cm².

Then apply LACURIS liquid so as to hold moisture, to get a good colour stability and to achieve improved hardness on the surface.

After 24 hours, retraction joints are formed.

The joints are finally sealed using LASTOIS MS.

Clean up

With plentyful clean water.

Data sheet

Density 1,40 ± 0,05 g/cc.

Temperature of work 5 to 35°C

Colour/s Grey, red, green, other colours upon request

% Solid content in weight Minor than 4950 mg (UNE 48.250-92/ASTM D-4060) TABER Abraser (Abrader) H-22/1000 g/1000 cycles

Performance

2 to 3 kg / sqm

Storage

2 years, in their original packagings, properly closed and protected from weather conditions.



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

Tel.: 981 602 111

Fax.: 981 601 508

Email: desarrollo@teais.es

síguenos en:

