



ACRILAIS, HIGH STRENGTH AND DURABILITY WATERPROOFING PAINT FOR OUTDOORS



Descripción

Waterproofing paint based on vinyl copolymers in watery dispersion for outdoors and indoors. Smooth finishes. Can be applied on fibrecement, cement mortars, plaster before suitable primer. Basic colours.

Aplicación

In facades, inner courtyards, party walls, balconies, large fortified towers, domes, etc.
Onto fibrocement boards, cement mortar renders, gypsum, plaster, etc by priming previously.

Surface preparation

Must be clean, without the presence of greases, oils, dust and loose particles, appearing perfectly dry.

Modes of application

Mix the contents of the bottle well, manually or with electric mixer low rpm 300-500 rpm.

- Apply With a brush, roller or spray.
- Apply the first coating by diluting up to 10 to 15% in weight in water.
- Once the first coating is dry(after at least 12 hours), apply a second or more



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email: desarrollo@teais.es

síguenos en:



coatings without diluting, in the same interval of time as for the first coating.
- The support must be clean, free of grease, dust or loose parts, being compact and perfectly dry, in case of using IMPRIMAIS MU primer.

Clean up

With plentiful clean water while the paint is fresh.

Data sheet

Density 1,54 Kg./Liter \pm 0,05 (varies depending on color).

Viscosity 40.000 \pm 10.000 mPs.a at 20°C

Dry upon touching 1 Hour /50 microns dry film/20°C/65% of H.R.

Totally dry 24 Hours /50 microns dry film/20°C/65% of H.R.

Dry for repainting 12 Hours /50 microns dry film/20°C/65% of H.R.

Aspects smooth, matt and semi-gloss.

Colour/white and colors according to color chart.

Performance

Smooth: 3 sqm per kg; Semi-gloss 3 to 5 sqm per kg

Storage

2 years, in their original packagings and properly closed, never under 5°C temperature, stored in a cool and a dry place.

Security



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teais.es

síguenos en:



Supplementary information:

EUH208: EUH208:Contains 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1). May produce an allergic reaction.

EUH210: EUH210:Safety data sheet available on request.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email.: desarrollo@teais.es

síguenos en:

