



# MADEPOIS LIQUIDO, FILLING PASTE AND ADHESIVE FOR WOOD.



## Descripción

Two-component epoxy adhesive in liquid shape that must be mixed just in the moment of using to join wooden pieces between them or with other materials such as concrete, stone, etc, The admixture has a maximum useful life of 20 minutes. After this time it hardens.

## Aplication

As an high power adhesive in the joint between pieces of wood, wood with concrete, wood with stone, etc. In works of reparation and refurbishment of wood, for small replacements where good mechanical resistances are required and also high adherence. For the refurbishment of beams or pillars made of wood using reinforcements based on fiberglass.

## Surface preparation

The support must be cleaned, free of greases, oils, loose parts and dry. It is recommendable to fit the surface mechanically, by projecting particles, milling, etc.

## Modes of application

It must be applied by brush, spatula or casting.  
Remove separately the content of both packages before mixing.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: desarrollo@teais.es

síguenos en:



- Mix manually or by a low revolution electric mixer (300-500) the content of the packages.
  - The mixing must be done in wide-mouth containers to increase the admixture useful life.
  - The mixing proportion is 6A: 4B on weight.
  - For mixing on weight per each 390 grs of A component are needed 260 grs of B component.
- Wet out abundantly (specially if the support is slightly wet). The surfaces must be joined by pressing them until achieve the perfect joint of the elements. The pieces must be keeping joined for at least 12 hours (20°C and 65% RH).
- The admixture must be used before 5-10 minutes(useful life).
- The temperature of the support must be over +10°C.
- As higher temperature the useful life of the product decreases. The advisable range of temperature is from 15°C to 20°C.
- Don't apply a coat thicker than 5 cm. If higher thickness are required is suitable to apply several layers leaving for 2 hours between layers (due the exothermic reaction produced by hot and the higher thickness of the layer, the wood can burn).
- Resistant to compression, traction and flexotraccion.
  - Resistant to chemical products and interior moisture.
  - High hardness and adherence on dry surfaces and a little wet.
  - Rootproof and waterproof.
- When a formwork is used and the product is apply by casting use polystirene as a barrier to avoid the adherence between both.

## Clean up

With TEAIS EPOXY SOLVENT.

## Data sheet

Density A component: 1.07 ± -0.05 gr/L B

Componen: 1.42 ± -0.05 gr/l

Dry upon touching < de 12 hours

Viscosity A Component: 30000 ± 15000 mPa.s at 20° Bcomponent: 4500 ± 3500 mPa.sat 20° C

Compressive resistance 50 N/mm<sup>2</sup>

Resistance to traction 40 N/mm<sup>2</sup>

Temperature of work From 8°C to 25°C

## Performance



According use

## Storage

---

Store in a dry and cool place, in their original packages, protecting them to extrem temperatures for a year maximum.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email.: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:

