



## Descripción

Caoutchou-based antirust primer

## Application

On ship hulls or elements which are in contact with marine waters.

## Surface preparation

Blast grade SA 2 1/2. Otherwise the surface must be free of rust, grease, dust or other pollution.

## Modes of application

Homogenize well the content of the package.

- A proper treatment of surface preparation must be done. The surface has to be free of rust in the moment of application. To achieve this, jets particles treatments are suitable.

It must be applied by brush, spray gun or airless.

- Don't apply it will be rain, strong winds, freezes or with bad weather.

## Clean up

With DISOLUAIS solvent.

# Data sheet

Colour/slight reddish and dark reddish

Density 1,27 Kg/L (+-) 0,05

Dry upon touching 30 m at 20° at 65% RH

Dry for repainting 6 h at 20° at 65% RH

Hard dry 3 h at 20° at 65% RH

Aspect semi-matt

Solid content in volume 40 %

Temperature of work from 8 to 30°C

## Performance

From 4 to 5 sqm per litre

## Storage

Store it in dry and cool places for 2 years maximum in its original package, tightly closed and protected from the weather.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:

